




FIT (flat milling)



LAP (stepwise milling)*



TAG (tongue and groove)*

Certificates / Approvals:

| | |
|---|---|
| CE mark | ■ |
| ISO 9001, ISO 14001 System certificates | ■ |
| Compatibility with EN 13165+A2 and EN 13172 | ■ |
| Environmental Declaration EPD (type III) | ■ |
| Environmental Certificate (type III) | ■ |
| CO2 footprint | ■ |
| (Leed & Breeam) Green Card | ■ |
| Atest PZH | |
| VOC | |
| Keymark certificate and quality label | ■ |
| Tests of thermal properties ITB | ■ |
| Fire classifications | ■ |
| ATG (50 mm - 200 mm) | ■ |
| KOMO | |
| Board in the product base SVT | |
| Board in the product base EPDM | ■ |
| SundaHUS | |
| BVB | |
| Swan- The Nordic Ecolabel | |
| Certificate for the system ETICS | ■ |
| Admitted to trading in the EU | ■ |

Product:

The termPIR® ETX insulation boards comprise of a PIR rigid foam thermal insulation core. Covered with a gas-permeable cladding (ETX), dedicated to external walls in the ETICS system with a thickened structure made of glass veil. The above boards should be fixed to the wall with the printed side, otherwise there may be problems with the durability of the façade.

Application:

Boards can be installed in one or multiple layers in an interlocking manner. Boards should fit tightly to each other. The substructure needs to be stable. Install mechanically with fasteners, glue or suspend - depending on the kind of substructure and type of waterproofing. Prevent from pulling the fasteners through the board. Secure against the impact of weather conditions. The boards are not load-bearing elements. Additional information is available in the Technical Catalogue at the website www.storyingsro.com.

* dimensions of boards with joint types are 2 to 4 % smaller

FIT (flat milling for 30 - 40 mm)

TAG tongue and groove from 80-250 mm)

Green
architecture



Information about product safety:

Information about substances contained in the product referred to in Art. 31 and 33 of the Regulation (CE) No.1907/2006 (REACH): Not applicable.

termPIR® ETX R-eco:

Product details:

| | |
|--|---|
| Kind of core: | Rigid polyisocyanurate foam (PIR) |
| Apparent PIR core density: | $\rho = 30 \text{ kg/m}^3$ |
| Declared heat transfer coefficient for lining: | for $(20 \leq d_N < 80 \text{ mm})$: $\lambda_D = 0,027 \text{ (W/m}\cdot\text{K)}$ |
| | for $(80 \leq d_N < 120 \text{ mm})$: $\lambda_D = 0,026 \text{ (W/m}\cdot\text{K)}$ |
| | for $(120 \leq d_N \leq 250 \text{ mm})$: $\lambda_D = 0,025 \text{ (W/m}\cdot\text{K)}$ |
| Standard board dimensions [mm]: | 600 x 1200 (minus the depth of the joint) |
| Available boards dimensions [mm]: | - |

Coefficient: U [W/m²·K], wg
 $U = 1 / (R_e + R_D + R_i)$

| For a given nominal thickness [mm]: Thermal resistance: R_D [m ² ·K/W] | for wall | 20 | 1,10 | 30 | 0,78 | 40 | 0,61 | 50 | 0,49 |
|---|----------|------------|------|------------|------|------------|------|------------|------|
| | or roof | 0,70 | 1,14 | 1,10 | 0,80 | 1,45 | 0,62 | 1,85 | 0,50 |
| for floor | | 1,10 | | 0,78 | | 0,61 | | 0,49 | |
| | | 60 | 0,42 | 70 | 0,36 | 80 | 0,31 | 90 | 0,28 |
| | | 2,20 | 0,42 | 2,55 | 0,37 | 3,05 | 0,31 | 3,45 | 0,28 |
| | | | 0,42 | | 0,36 | | 0,31 | | 0,28 |
| | | 100 | 0,25 | 110 | 0,23 | 120 | 0,20 | 130 | 0,19 |
| | | 3,80 | 0,25 | 4,20 | 0,23 | 4,80 | 0,20 | 5,20 | 0,19 |
| | | | 0,25 | | 0,23 | | 0,20 | | 0,19 |
| | | 140 | 0,17 | 150 | 0,16 | 160 | 0,15 | 170 | 0,14 |
| | | 5,60 | 0,17 | 6,00 | 0,16 | 6,40 | 0,15 | 6,80 | 0,14 |
| | | | 0,17 | | 0,16 | | 0,15 | | 0,14 |
| | | 180 | 0,14 | 190 | 0,13 | 200 | 0,12 | 210 | 0,12 |
| | | 7,20 | 0,14 | 7,60 | 0,13 | 8,00 | 0,12 | 8,40 | 0,12 |
| | | | 0,14 | | 0,13 | | 0,12 | | 0,12 |
| | | 220 | 0,11 | 230 | 0,11 | 240 | 0,10 | 250 | 0,10 |
| | | 8,80 | 0,11 | 9,20 | 0,11 | 9,60 | 0,10 | 10,00 | 0,10 |
| | | | 0,11 | | 0,11 | | 0,10 | | 0,10 |

| | | |
|--|--|--------------------------------|
| Compressive strength at 10% of deformation: | $\sigma \geq 120 \text{ kPa}$ | $20 \leq d_N < 250 \text{ mm}$ |
| Tensile strength perpendicular to faces: | for $(20 \leq d_N < 50 \text{ mm})$: NPD | |
| | for $(50 \leq d_N \leq 250 \text{ mm})$: $\geq 80 \text{ kPa}$, TR80 | |
| Water vapour transmission: | $\mu = (90 \div 170)$ | |
| Dimensional stability: | for $(20 \leq d_N < 50 \text{ mm})$: DS(70,-)1 | |
| | for $(50 \leq d_N \leq 250 \text{ mm})$: DS(-20,-)2 / DS(70,90)3 | |
| Reaction to fire (of the product as placed on the market): | 20-49: F class, 50-250: E class | |

Parameters of the termPIR® ETX board in the ETICS facade system (for a board with a minimum thickness of 50 mm):

| | |
|-------------------------------|---|
| Reaction to fire (end of use) | B-s1,d0 Class |
| Fire spread: | NRO, „non-fire spreading product” |
| Certifications: | The product has had issued for it a Certificate of Conformity, based on a European Technical Approval, according to the ETAG 004 Guideline. |

Buildings:

Intended use of the board

| | | |
|------------------------------------|--|---|
| residential, high density housing | on rafter insulation system on pitched roofs | |
| residential | under rafter insulation system on pitched roof | |
| residential, retail and industrial | build Up Roofs [BUR] - Flat roofs, mechanically fastened | |
| residential, retail and industrial | build Up Roofs [BUR] - Flat roofs, adhesive or glued systems | |
| residential, retail and industrial | triple layered external walls - cavity walls | |
| residential, retail and industrial | double layered external walls - ETICS system | ■ |
| residential, retail and industrial | basement and foundation walls | |
| residential, retail and industrial | partition walls | |
| residential, retail and industrial | slabs between floors | |
| residential, retail and industrial | ground floor slabs | |
| livestock, industrial | suspended ceilings - high pressure washable | |
| existing, historic, stair-cores | internal wall insulation | |
| prefabricated concrete walls | highly resistant to corrosion caused by concrete | |

■ the board recommended for use